

Experiment for Bending Analysis of 3-phase Composite Plate in Ship Structure

Nguyen Dinh Duc^{1,*}, Dinh Khac Minh²

¹University of Engineering and Technology, VNU, E3-144 Xuan Thuy, Cau Giay, Hanoi, Vietnam

²Shipbuilding Science and Technology Institute, Hanoi

Received 9 June 2010

Abstract. Composite is a material composed of two or more component materials to obtain better properties. 3-phase composite is usually added with reinforced fibers and particles. This report presents an experimental study on the bending of some 3-phase composite plates for Vietnam's shipbuilding industry. The studied composite is made of polyester matrix, glass fiber and titanium dioxide particle (TiO_2). The numerical study, in which the interaction between the matrix and particle is taken into account, shows good agreement with the experiment.

1. Introduction

To improve both the mechanical and physical properties, composite can be reinforced simultaneously with both fibers and particles, thus 3-phase composite appears.

The bending problem of anisotropic plate and shell is studied in [1,2]. The bending of composite is studied in [2,3]. In [4], we investigate the bending problem for 3-phase composite, taking into account the shear effect, and in [5] we take into account the creep effect.

Recently, the present authors have published some experiments to determine the elastic modules for 3-phase composite with different volume ratio of fiber and particle. Our purpose in this paper is to continue the experiments, for the bending of 3-phase composite plates used in Vietnam's shipbuilding. The material is made of polyester matrix, reinforced by glass fibers and titanium dioxide particles. The formulas used for the calculation are from [6-8] and [4-5,9].

2. Preparation of the samples

The samples' dimension is 500mmx300mm. It is made of 6 plies, the stack sequence is $[0^\circ/+45^\circ/-45^\circ/+45^\circ/-45^\circ/90^\circ]$. The plate's thickness is 5.5 mm. The material's components are AKAVINA polyester, glass fiber imported from Korea, and titanium dioxide particle imported from Australia.

The test is done with test machine SANS following method BS EN ISO 527-1: 1997. Room temperature is $(20^\circ\text{C}\pm 5^\circ\text{C})$, humidity is $65\%\pm 20\%$, the samples are manufactured according to

* Corresponding author. E-mail: ducnd@vnu.edu.vn

standard TCVN 6282:2008 [10]. The experiments were done in the Laboratory of the Shipbuilding Science and Technology Institute - Nha Trang University.



Fig. 1. Bending test for 3-phase composite plate.

3. Deflection equation

For orthotropic plates material, the stress-strain relationship is [1-3]:

$$\begin{cases} \sigma_{11} = A_{11}\varepsilon_{11} + A_{12}\varepsilon_{22} \\ \sigma_{22} = A_{22}\varepsilon_{22} + A_{12}\varepsilon_{11} \\ \sigma_{66} = A_{66}\varepsilon_{66} \\ \sigma_{44} = A_{44}\varepsilon_{44} \\ \sigma_{55} = A_{55}\varepsilon_{55} \end{cases} \quad (1)$$

Here

$$A_{11} = \frac{E_{11}}{1 - \nu_{12}\nu_{21}}; A_{22} = \frac{E_{22}}{1 - \nu_{12}\nu_{21}}; A_{12} = \frac{E_{11}\nu_{21}}{1 - \nu_{12}\nu_{21}} = \frac{E_{22}\nu_{12}}{1 - \nu_{12}\nu_{21}}; A_{66} = G_{12} \quad (2)$$

Our purpose is to determine the deflection for 3-phase composite plate. As we mentioned above, the deflection equation for orthotropic plates is described in [1-3,11]. When shear strain is taken into account, the deflection equation is expressed by three differential equations [4]:

$$\begin{cases} \frac{\partial \varphi}{\partial x} + \frac{\partial \psi}{\partial y} = -\frac{z}{I_2(h)} \\ D_x \frac{\partial^3 w}{\partial x^3} + (D_1 + 2D_{x,y}) \frac{\partial^3 w}{\partial x \partial y^2} - \frac{12}{h^3} I_1 \left[\frac{D_y}{A_{55}} \frac{\partial^2 \varphi}{\partial x^2} + \frac{D_{xy}}{A_{55}} \frac{\partial^2 \varphi}{\partial y^2} + \frac{(D_1 + D_{xy})}{A_{44}} \frac{\partial^2 \varphi}{\partial x \partial y} \right] + I_2 \varphi = 0 \\ D_y \frac{\partial^3 w}{\partial y^3} + (D_1 + 2D_{x,y}) \frac{\partial^3 w}{\partial x^2 \partial y} - \frac{12}{h^3} I_1 \left[\frac{D_y}{A_{44}} \frac{\partial^2 \psi}{\partial y^2} + \frac{D_{xy}}{A_{44}} \frac{\partial^2 \psi}{\partial x^2} + \frac{(D_1 + D_{xy})}{A_{55}} \frac{\partial^2 \psi}{\partial x \partial y} \right] + I_2 \psi = 0 \end{cases} \quad (3)$$

The set of equation (3) is the basic set to determine the plate's deflection when shear strain is taken into account. The coefficients $A_{11}, A_{22}, A_{12}, A_{66}, A_{44}, A_{55}$ are used to determine D_{ij} in (3). These coefficients can be calculated from the elastic modules of the material. Note that with the ratio between the plate's length and thickness equals $500/5,5=91$, our plates are considered to be very thin and shear effect can be neglected, thus we can use the deflection equation mentioned in [1,2,11] which is not repeated here.

4. Determine the elastic modules for 3-phase composite plate

The elastic modules for 3-phase composite are calculated step by step by 2-phase model as in [5,6,8]. We also carried out the experiments for 3-phase composite's elastic modules [9].

After determining (\bar{G}, \bar{K}) or $(\bar{E}, \bar{\nu})$ for effective matrix, the elastic modules for 3-phase composite can be calculated as below [6,7]:

$$E_{11} = \xi_a E_a + (1 - \xi_a) \bar{E} + \frac{8\bar{G}\xi_a(1 - \xi_a)(\nu_a - \bar{\nu})}{2 - \xi_a + \bar{\chi}\xi_a + (1 - \xi_a)(\chi_a - 1)\frac{\bar{G}}{G_a}}$$

$$E_{22} = \left[\frac{\nu_{21}^2}{E_{11}} + \frac{1}{8\bar{G}} \left[\frac{2(1 - \xi_a)(\bar{\chi} - 1) + (\chi_a - 1)(\bar{\chi} - 1 + 2\xi_a)\frac{\bar{G}}{G_a}}{2 - \xi_a + \bar{\chi}\xi_a + (1 - \xi_a)(\chi_a - 1)\frac{\bar{G}}{G_a}} + 2 \frac{\bar{\chi}(1 - \xi_a) + (1 + \xi_a\bar{\chi})\frac{\bar{G}}{G_a}}{\bar{\chi} + \xi_a + (1 - \xi_a)\frac{\bar{G}}{G_a}} \right] \right]^{-1}$$

$$\nu_{21} = \bar{\nu} - \frac{(\bar{\chi} + 1)(\bar{\nu} - \nu_a)\xi_a}{2 - \xi_a + \bar{\chi}\xi_a + (1 - \xi_a)(\chi_a - 1)\frac{\bar{G}}{G_a}}; G_{12} = \bar{G} \frac{1 + \xi_a + (1 - \xi_a)\frac{\bar{G}}{G_a}}{1 - \xi_a + (1 + \xi_a)\frac{\bar{G}}{G_a}};$$

$$G_{23} = \bar{G} \frac{\bar{\chi} + \xi_a + (1 - \xi_a)\frac{\bar{G}}{G_a}}{(1 - \xi_a)\bar{\chi} + (1 + \bar{\chi}\xi_a)\frac{\bar{G}}{G_a}} \tag{4}$$

Here $G_a = \frac{0.5E_a}{(1 + \mu_a)}; G_c = \frac{0.5E_c}{(1 + \mu_c)}; \bar{E} = \frac{9\bar{K}\bar{G}}{3\bar{K} + \bar{G}}; \bar{\nu} = \frac{3\bar{K} - 2\bar{G}}{6\bar{K} - 2\bar{G}}; \bar{\chi} = 3 - 4\bar{\nu}$ (5)

and \bar{G}, \bar{K} are the elastic modules of the effective matrix

$$\bar{G} = G_m \frac{1 - \xi_c(7 - 5\nu_m)H}{1 + \xi_c(8 - 10\nu_m)H}; \bar{K} = K_m \frac{1 + 4\xi_c G_m L(3K_m)^{-1}}{1 - 4\xi_c G_m L(3K_m)^{-1}} \tag{6}$$

Here $L = \frac{K_c - K_m}{K_c + \frac{4G_m}{3}}; H = \frac{G_m/G_c - 1}{8 - 10\nu_m + (7 - 5\nu_m)\frac{G_m}{G_c}}$ (7)

5. Experiment result

In the experiment, the two shorter edges of the plate are clamped, while the two longer edges are free. The concentrated force is increased with time (Figure 1). There are two set of samples: set A (20% fiber and 10% particle) and set B (20% fiber and 20% particle).

The test result for maximum deflection at the plate's center is given in Table 1.

Table 1. Comparison between analysis and experiment for bending deflection

3-phase composite	Concentrate force					Ultimate deflection
	1kN	3kN	6kN	10kN		
10%TiO ₂ + 20%W800 + 70% AKAVINA polyester (sample type A)	Deflection (mm)					
	Experiment	7,6	14,2	20,8	32,4	34,3
	Analysis	8,1	15,3	22,2	34,2	-
	Error %	6,57	7,75	6,73	5,56	-
20%TiO ₂ + 20%W800 + 60% AKAVINA polyester (sample type B)	Deflection (mm)					
	Experiment	6,0	12,3	19,2	29,0	33,0
	Analysis	6,5	13,4	21,0	31,6	-
	Error %	8,33	8,94	9,30	8,96	-

Note: * is the average result after 5 tests for one sample type.

From the result in Table 1, we can come to a conclusion: adding fiber and particle can decrease the plate's deflection. When the added material's volume ratio is increased, the deflection is decreased. Moreover, compare to increasing the particle's volume ratio, increasing the fiber's volume ratio can decrease the deflection faster.

6. Conclusion

In this paper we report the experiments for bending problem of 3 phase composite made of polyester matrix, glass fiber and titanium dioxide particle.

The experiment result shows that the particle's volume ratio doesn't affect the deflection much, while fiber and the plate's thickness affect it better.

Comparison between analysis and experiment show good agreement.

The authors would like to thank to the Laboratory of the Shipbuilding Science and Technology Institute - Nha Trang University for their help in the experiment.

The results of researching presented in the paper have been performed according to scientific research project of Vietnam National University, Hanoi (VNU, Hanoi), coded QGTD.09.01.

Referentes

- [1] S. Timoshenko, S. Krieger, *Theory of Plates and Shells*, Mc Graw-Hill Book Company, NY. 1959.
- [2] J.N. Reddy, *Mechanics of Laminated Composite Plates and Shells: Theory and Analysis*, CRC Press, 2004
- [3] A.K. Malmeicter, V.P. Tamuz, G.A. Teterc, *Strength of composite materials*, Riga, "Zinatie", 1980.
- [4] Nguyen Dinh Duc, Dinh Khac Minh, Bending analysis of three-phase polymer composite plates reinforced by glass fibers and Titanium oxide particles, *J. Computational Materials Sciences*, vol. 49, No 4 (2010) 194.

- [5] Dinh Khac Minh, Pham Van Thu, Nguyen Dinh Duc, Bending of three phase composite plate with creep effect, *Proceeding of The International Conference on Engineering Mechanics and Automation – ICEMA 2010, Hanoi*, (2010) 53.
- [6] Nguyen Hoa Thinh, Nguyen Dinh Duc, *Composite material: Mechanics and Technology*, Vietnam Science and Technology Publishing House, Hanoi, (2002) 364p.
- [7] G.A. Vanin, *Micro-Mechanics of composite materials*, “Nauka Dumka”, Kiev, 1985.
- [8] G.A. Vanin, Nguyen Dinh Duc, The theory of spherofibre composite. 1: The input relations, hypothesis and models, *J. Mechanics of composite materials*, vol.32, No.3 (1996) 291.
- [9] Nguyen Dinh Duc, Dinh Khac Minh, *Experimental study on mechanical properties for 3 phase polymer composite reinforced by glass fibers and titanium oxide particles* (Submitted, 2010).
- [10] *Vietnamese standards code TCVN 6282:2008 for testing and manufacturing ship made of composite polymer reinforced by glass fibbers*, Transportation Publishing House, Hanoi, 2008.
- [11] Tran Ich Thinh, *Composite material, mechanics and structure*, Vietnam Education Publishing House, Hanoi, 1994.